

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1-22 (cancelled).

23 (currently amended). A polymer blend comprising:

(a) 1 - 99% by weight of a copolymer of ethylene and an alpha olefin having from 3 to 10 carbon atoms, said copolymer having

(i) a density in the range 0.905 to 0.940 g cm^{-3} ,

(ii) a melt elastic modulus G' ($G'' = 500 \text{ Pa}$) in the range 10 to 150 Pa,

and

(iii) a melt index ($190^{\circ}\text{C}/2.16 \text{ kg}$) in the range 5 to 50 g/10 ml, and

(b) from 1 - 99% by weight of a low density polyethylene (LDPE) comprising a homopolymer of ethylene having a density from 0.914 to 0.928 g cm^{-3} ,

wherein the sum of (a) and (b) is 100 %.

24 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) has a density in the range 0.907 to 0.915 g cm^{-3} .

25 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) has a melt index in the range 12 to 50 g/10 ml.

26 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) has a melt elastic modulus G' in the range 11 to 90 Pa.

27 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) has a flow activation energy (E_a) in the range 28 to 50 kJ/mol.

28 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) has a M_w/M_n in the range 2 to 3.5.

29 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) exhibits more than one differential scanning calorimetry (DSC) melting peaks between 30° and 150°C.

30 (previously presented). A polymer blend according to claim 23 wherein the LDPE of component (b) has a melt index in the range 0.1 to 25 g/10 ml.

31 (previously presented). A polymer blend according to claim 23 wherein the LDPE of component (b) has a melt elastic modulus G' in the range 80 to 200 Pa.

32 (previously presented). A polymer blend according to claim 23 wherein the ratio of component (a) to component (b) is in the range 60:75 to 40:25 by weight.

33 (previously presented). A polymer blend according to claim 23 wherein the blend has a melt elastic modulus G' in the range 30 to 200 Pa.

34 (previously presented). A polymer blend according to claim 33 wherein the blend has a melt elastic modulus G' in the range 30 to 200 Pa.

35 (previously presented). A polymer blend according to claim 34 wherein the blend has a melt elastic modulus G' in the range 60 to 120 Pa.

36 (previously presented). A polymer blend according to claim 35 wherein the melt elastic modulus G' is in the range 75-100 Pa.

37 (currently amended). A polymer blend comprising:

(a) 1 - 99% by weight of a copolymer of ethylene and an alpha olefin having from 3 to 10 carbon atoms, said copolymer having

(iv) a density in the range 0.905 to 0.940 g cm^{-3} ,

(v) a melt elastic modulus G' ($G'' = 500 \text{ Pa}$) in the range 10 to 150 Pa,

and

(vi) a melt index ($190^\circ\text{C}/2.16 \text{ kg}$) in the range 5 to 50 g/10 ml, and

(b) from 1 - 99% by weight of a low density polyethylene (LDPE) comprising a homopolymer of ethylene having a density from 0.914 to 0.928 g cm^{-3} , and


(c) from 0 - 98% by weight of a copolymer of ethylene and an alpha-olefin having 3 to 10 carbon atoms or a low density polyethylene (LDPE),

wherein the sum of (a), (b) and (c) is 100 %.

38 (previously presented). A polymer blend according to claim 23 wherein the copolymer of component (a) is prepared by use of a catalyst system comprising a transition metal compound.

39 (previously presented). A polymer blend according to claim 38 wherein the transition metal compound is a metallocene.

40 (currently amended). A polymer blend according to claim 39 wherein the metallocene has the general formula



wherein:-

R' each occurrence is independently selected from hydrogen, hydrocarbyl, silyl, germyl, halo, cyano, and combinations thereof, said R' having up to 20 nonhydrogen atoms, and optionally, two R' groups $\{_1$ where R' is not hydrogen, halo or cyano $\}_1$ together form a divalent derivative thereof connected to adjacent positions of the cyclopentadienyl ring to form a fused ring structure;

X is a neutral η^4 bonded diene group having up to 30 non-hydrogen atoms, which forms a π -complex with M;

Y is -O-, -S-, -NR^{*}-, -PR^{*}-;

M is titanium or zirconium in the + 2 formal oxidation state;

Z^{*} is SiR^{*}₂, CR^{*}₂, SiR^{*}₂SIR^{*}₂, CR^{*}₂CR^{*}₂, CR^{*}=CR^{*}, CR^{*}₂SIR^{*}₂, or

GeR^{*}₂, wherein:

R^{*} each occurrence is independently hydrogen, or a member selected from hydrocarbyl, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said

R^{*} having up to 10 non-hydrogen atoms, and optionally, two R^{*} groups from Z^{*} (when R^{*} is not hydrogen), or an R^{*} group from Z^{*} and an R^{*} group from Y form a ring system.

41 (previously presented). A polymer blend according to claim 38 wherein the copolymer is prepared in the gas phase.

42 (previously presented). A polymer blend according to claim 23 wherein the low density polyethylene (LDPE) of component (b) is prepared by a high pressure process.

43 (currently amended). An extrusion coating comprising a polymer blend comprising:

(a) 1 - 99% by weight of a copolymer of ethylene and an alpha olefin having from 3 to 10 carbon atoms, said copolymer having

- (i) a density in the range 0.905 to 0.940 g cm⁻³,
 - (ii) a melt elastic modulus G' (G'' = 500 Pa) in the range 10 to 150 Pa, and
 - (iii) a melt index (190°C/2.16 kg) in the range 5 to 50 g/10 ml, and
- (b) from 1 - 99% by weight of a low density polyethylene (LDPE) comprising a homopolymer of ethylene having a density from 0.914 to 0.928 g cm³ cm⁻³,
wherein the sum of (a) and (b) is 100 %.

44 (currently amended). An extrusion coating comprising a polymer blend comprising:

- (a) 1-99% by weight of a copolymer of ethylene and an alpha olefin having from 3 to 10 carbon atoms, said copolymer having
 - (i) a density in the range 0.905 to 0.940 g ~~cm~~³ cm⁻³,
 - (ii) a melt elastic modulus G' (G'' = 500 Pa) in the range 10 to 150 Pa,and
 - (iii) a melt index (190°C/2.16 kg) in the range 5 to 50 g/10 ml,
- (b) from 1-99% by weight of a low density polyethylene (LDPE) comprising a homopolymer of ethylene having a density from 0.914 to 0.928 g cm⁻³, and
- (c) from 0.98% by weight of a copolymer of ethylene and an alpha olefin having 3 to 10 carbon atoms or a low density polyethylene (LDPE) polymer wherein the sum of (a), (b) and (c) is 100%.